

Edelstahlstandards - Weltweit
Universal Stainless Steel Standards

Deutschland Germany		England U.K.	EU	Frankreich France	Italien Italy	Spanien Spain
W.N. 17077	DIN 17006	BSI	EURONORM	AFNOR	UNI	UNE
1.4000	X 6 Cr 13	403S17	X 6 Cr 13	Z 6 C 13	X 6 Cr 13	
1.4000	X 6 Cr 13	403S17	X 10 Cr 13	Z 12 C 13	Z 12 Cr 13	
1.4006	X 10 Cr 13		X 12 Cr 13			
1.4024	X 15 Cr 13					
1.4000	X 6 Cr 13	410S21	X 12 Cr 13	Z 10 C 13	X 12 Cr 13	X 12 Cr 13
1.4006	X 10 Cr 13			Z 12 C 13		
1.4024	X 15 Cr 13					
1.4002	X 6 CrAl 13	405S17	X 6 CrAl 13	Z 6 CA 13	X 6 CrAl 13	X 6 CrAl 13
1.4104	X 6 CrMoS17	441S01	X12CrMoS17	Z13 CF 17	X 10 CrS 17	
1.4301	X 5 CrNi 18 10	304S15	X 6 CrNi 18 10	Z 6 CN 18-09	X 5 CrNi 1810	X 6 CrNi 19-10
1.4303	X 5 CrNi 18 12	304S16				
1.4305	X 10 CrNiS 18 9	303S21	X 10 CrNiS 18 9	Z 10 CNF18-09	X 10 CrNiS 1809	X 10 CrNiS 18-09
1.4306	X 2 CrNi 18 11	304S11	X 3 CrNi 18 10	Z 2 CN 18-10	X 2 CrNi 1911	X 2 CrNi 19-10
1.4310	X 12 CrNi 17 7	301S21	X 12 CrNi 17 7	Z 12 CN 17-07	X 12 CRNi 1707	X 12 CrNi 17-07
1.4311	X 2 CrNiN 18 10			Z 2 CN 18-10-Az	X 2 CrNiN 1811	
1.4319	X 5 CrNi 18 7	302S25	X 10 CrNi 18 9	Z 10 CN 18-09	X 10 CrNi 1809	X 10 CrNi 18-09
1.4401	X 5 CrNiMo 17 12 2	316S31	X 6 CrNiMo 17 12 2	Z 6 CND 17-11	X 5 CrNiMo 1712	X 6 CrNiMo 17-12-03
1.4404	X 2 CrNiMo 17 13 2	316S11	X 3 CrNiMo 17 12 2	Z 2 CND 17-12	X 2 CrNiMo 1712	X 2 CrNiMo 17-12-03
1.4406	X 2 CrNiMoN 17 12 2			Z 2 CND 17-12-Az	X 2 CrNiMoN 1712	
1.4427	X 12 CrNiMoS 18 11					
1.4429	X 2 CrNiMoN 17 13 3			Z 2 CND 17-13-Az	X 2 CrNiMoN 1713	
1.4435	X 2 CrNiMo 18 14 3	316S13	X 3 CrNiMo 17 13 3	Z 2 CND 17-13	X 2 CrNiMo 1713	X 2 CrNiMo 17-12-03
1.4436	X 5 CrNiMo 17 13 3	316S33	X 6 CrNiMo 17 13 3	Z 6 CND 17-12	X 5 CrNiMo 1713	X 6 CrNiMo 17-12-03
1.4438	X 2 CrNiMo 18 16 4	317S12	X 3 CrNiMo 18 16 4	Z 2 CND 19-15	X 2 CrNiMo 1815	
1.4438	X 2 CrNiMo 18 16 4	317S12	X 3 CrNiMo 18 16 4	Z 2 CND 19-15	X 2 CrNiMo 1816	
1.4460	X 8 CrNiMo 27 5					
1.4462	X 2 CrNiMoN 22 5					
1.4501	X 3 CrNiMoN 25 7			Z 3 CND 25-06Az		
1.4512	X 6 CrTi 12	409S19	X 5 CrTi 12	Z 6 CT 12	X 6 CrTi 12	
1.4541	X 6 CrNiTi 18 10	321S31	X 6 CrNiTi 18 10	Z 6 CNT 18-10	X 6 CrNiTi 1811	X 6 CrNiTi 18-11
1.4878	X 12 CrNiTi 18 9					
1.4550	X 6 CrNiNb 18 10	347S31	X 6 CrNiNb 18 10	Z 6 CNNb 18-10	X 6 CrNiNb 1811	X 6 CrNiNb 18-11
1.4571	X 6 CrNiMoTi 17 12 2	320S31	X 6 CrNiMoTi 17 12 2	Z 6 CNDT 17-12	X 6 CrNiMoTi 1712	X 6 CrNiMoTi 17-12-03
1.4573	X 10 CrNiMoTi 18 12	320S33	X 6 CrNiMoTi 17 13 3		X 6 CrNiMoTi 1713	X 6 CrNiMoTi 17-12-03
1.4580	X 6 CrNiMoNb 17 12 2		X 6 CrNiMoNb 17 12 2	Z 6 CNDNb 17-12	X 6 CrNiMoNb 1712	
1.4583	X 10 CrNiMoNb 18 12		X 6 CrNiMoNb 17 13 3		X 6 CrNiMoNb 1713	
1.4713	X 10 CrAl 7		X 10 CrAl 7	Z 8 CA 7		
1.4724	X 10 CrAl 13				X 10 CrAl 12	
1.4742	X 10 CrAl 19		X 10 CrSiAl 18			
1.4821	X 20 CrNiSi 25 4					
1.4828	X 15 CrNiS 20 12	309S24	X 15 CrNi 23 13	Z 15 CN 24-13	X 16 CrNi 2314	
1.4841	X 15 CrNiSi 25 20		X 15 CrNiSi 25 20	Z 12 CNS 25-20	X 16 CrNiSi 2520	
1.4842	X 12 CrNi 25 20		X 6 CrNi 25 20	Z 12 CN 25-20	X 5 CrNi 2520	
1.4845	X 12 CrNi 25 21	310S24			X 22 CrNi 2520	
1.4864	X 12 NiCrSi 36 16			Z 12 NCS 35-16		
1.4939				Z 12 CNDV 12-02		
¹⁾ austenitisch					¹⁾ austenitic grades	
²⁾ austenitisch-ferritisch					²⁾ austenitic-ferritic grades	
³⁾ ferritisch					³⁾ ferritic grades	

Alle Angaben nach bestem Wissen, aber OHNE Gewähr.

Information provided to the best of our knowledge, but WITHOUT guaranty.

Edelstahlstandards - Weltweit
Universal Stainless Steel Standards

Deutschland Germany		U.S.A.	EU	Japan	Russland Russia	Schweden Sweden
W.N. 17077	DIN 17006	AISI	EURONORM	JIS	GOST	SIS
1.4000	X 6 Cr 13	410 S ³⁾	X 6 Cr 13	SUS 410S		23 01
1.4000	X 6 Cr 13	403 ³⁾	X 10 Cr 13	SUS 403		23 02
1.4006	X 10 Cr 13		X 12 Cr 13			
1.4024	X 15 Cr 13					
1.4000	X 6 Cr 13	410 ³⁾	X 12 Cr 13	SUS 410	08Jh13	23 02
1.4006	X 10 Cr 13					
1.4024	X 15 Cr 13					
1.4002	X 6 CrAl 13	405 ³⁾	X 6 CrAl 13	SUS 405		
1.4104	X 6 CrMoS17	430 F ³⁾	X12CrMoS17	SUS 430F		23 83
1.4301	X 5 CrNi 18 10	304 ¹⁾	X 6 CrNi 18 10	SUS 304	08KH18N10	23 32
1.4303	X 5 CrNi 18 12				06KH18N11	
1.4305	X 10 CrNiS 18 9	303 ¹⁾	X 10 CrNiS 18 9	SUS 303		23 46
1.4306	X 2 CrNi 18 11	304 L ¹⁾	X 3 CrNi 18 10	SUS 304L	03KH18N11	23 52
1.4310	X 12 CrNi 17 7	301 ¹⁾	X 12 CrNi 17 7	SUS 301		23 31
1.4311	X 2 CrNiN 18 10			SUS 304LN		23 71
1.4319	X 5 CrNi 18 7	302 ¹⁾	X 10 CrNi 18 9	SUS 302	12KH18N9	23 31
1.4401	X 5 CrNiMo 17 12 2	316 ¹⁾	X 6 CrNiMo 17 12 2	SUS 316		23 47
1.4404	X 2 CrNiMo 17 13 2	316 L ¹⁾	X 3 CrNiMo 17 12 2	SUS 316L		23 48
1.4406	X 2 CrNiMoN 17 12 2			SUS 316LN	03KH16N15M3	
1.4427	X 12 CrNiMoS 18 11	316 F ¹⁾				
1.4429	X 2 CrNiMoN 17 13 3				08KH17N13M2T 10KH17N13M2T	23 75
1.4435	X 2 CrNiMo 18 14 3	316 L ¹⁾	X 3 CrNiMo 17 13 3			23 53
1.4436	X 5 CrNiMo 17 13 3	316 ¹⁾	X 6 CrNiMo 17 13 3	SUS 316		23 43
1.4438	X 2 CrNiMo 18 16 4	317 L ¹⁾	X 3 CrNiMo 18 16 4	SUS 317L		23 67
1.4438	X 2 CrNiMo 18 16 4	317 L ¹⁾	X 3 CrNiMo 18 16 4	SUS 317L		23 67
1.4460	X 8 CrNiMo 27 5	329 ¹⁾		SUS 329/1	08KH18N12B	23 24
1.4462	X 2 CrNiMoN 22 5	UNS31803 ²⁾				
1.4501	X 3 CrNiMoN 25 7	UNS32760 ²⁾		12Kh13		
1.4512	X 6 CrTi 12	409 ³⁾	X 5 CrTi 12	SUH 409		
1.4541	X 6 CrNiTi 18 10	321 ¹⁾	X 6 CrNiTi 18 10	SUS321	12KH18N10T	23 37
1.4878	X 12 CrNiTi 18 9					
1.4550	X 6 CrNiNb 18 10	374 ¹⁾	X 6 CrNiNb 18 10	SUS 347		23 38
1.4571	X 6 CrNiMoTi 17 12 2	316Ti	X 6 CrNiMoTi 17 12 2		08KH17N13M2T 10KH17N13M2T	23 50
1.4573	X 10 CrNiMoTi 18 12		X 6 CrNiMoTi 17 13 3		08KH16N13M2B	
1.4580	X 6 CrNiMoNb 17 12 2		X 6 CrNiMoNb 17 12 2		09KH16N15M3B	
1.4583	X 10 CrNiMoNb 18 12		X 6 CrNiMoNb 17 13 3			
1.4713	X 10 CrAl 7		X 10 CrAl 7		10Kh13SYu	
1.4724	X 10 CrAl 13				15Kh18SYu	
1.4742	X 10 CrAl 18		X 10 CrSiAl 18			
1.4821	X 20 CrNiSi 25 4					
1.4828	X 15 CrNiS 20 12	309 ¹⁾	X 15 CrNi 23 13	SUH 309		
1.4841	X 15 CrNiSi 25 20	314 ¹⁾	X 15 CrNiSi 25 20			
1.4842	X 12 CrNi 25 20	310 S ¹⁾	X 6 CrNi 25 20	SUS 301S	20KH25N20S2	23 61
1.4845	X 12 CrNi 25 21	310 ¹⁾		SUH 310	10KH23N18	
1.4864	X 12 NiCrSi 36 16	330 ¹⁾		SUH 330	08KH18N10T	
1.4939		904 ¹⁾				
¹⁾ austenitisch				¹⁾ austenitic grades		
²⁾ austenitisch-ferritisch				²⁾ austenitic-ferritic grades		
³⁾ ferritisch				³⁾ ferritic grades		

Alle Angaben nach bestem Wissen, aber OHNE Gewähr.

Information provided to the best of our knowledge, but WITHOUT guaranty.